CHARISMA



SPC 4.4 MM, 12 MIL

Construction	SPC, Stone Polymer Composite, Rigid Core		
Classification	ASTM F3261, Class 1, Type B, Grade 1, Class B		
Dimensions	6" Wide x 36" Long, 152 mm x 915 mm		
Overall Thickness	4.4 mm (Includes 1 mm IXPE pad)		
Attached Pad	1 mm IXPE Sound Abatement Pad		
Wear Layer	12 mil		
Finish Coat	Polyurethane		
Texture	Embossed		
Edge Profile	4-Sided Micro Bevel		
Packaging	24 sf/carton - 54 cartons/pallet - 1296 sf/pallet		

Installation & Maintenance

Angle / Angle, Float

Expansion & Transition: 1/4" Expansion required at perimeter and at all vertical surfaces. Transition required for rooms larger than 50' W x 50' L.

Ambient & Surface Temperature at Installation: 60 - 85 Degrees Fahrenheit

Maintenance: No Polish, Fresh Floors by Taylor

Test Method & Requirements		
Resilient Floor in Modular Format	ASTM F3261	Pass
Thickness (with Pad)	ASTM F386/ (387)	Pass
Wear Layer Thickness	ASTM F410	Pass
Stain/Chemical Resistance	ASTM F925	Pass
Resistance to Heat Color Change	ASTM F1514	Pass
Resistance to Light Color Change	ASTM F1515	Pass
Residual Indentation	ASTM F1914	Pass
Size & Squareness	ASTM F2055	Pass
Dimensional Stability w/Exposure to Heat	ASTM F2199	Pass
Dimensional Stability w/Exposure to Heat	ISO 23999	Pass
Determination of Geometrical Characteristics	ISO 24337	Pass
Static Coefficient of Friction Polished Surface	ASTM D2047	Exceeds Standard
Static Load Limit	ASTM F970	PASS >250 LBS
Flammability/Radiant Flux	ASTM E648	Class I
Smoke Density	ASTM E662	Pass
Impact Insulation Class IIC	ASTM E492*	
Sound Transmission Class STC	ASTM E90*	

^{*}The flooring assembly dictates IIC, STC, HIIC, and Low IIC results; contact your representative for specific testing.

Health & Environmental

FloorScore Certified # SCS-FS-06263

Phthalate-Free














Warranty

5 Yr Light Commercial, 5 Yr Multi-Family, 25 Yr Residential

Accessories

Trims: T Mold, Reducer, End Cap, Stair Nose, Quarter Round
QNose Stair Nosing

